

地址：山东省淄博市高青县常家镇

Address: ChangJiaZhen, GaoqingCounty, ZiboCity, ShandongProvince

电话/Phone: +86-0533-6992006. 传真/Fax: +86-0533-6992006

HY 70A

用途/Application:

本产品可用于蜡烛的生产加工。

This product can be used for the production and processing of candles.

性能/Performance:

本产品纯度高、润滑性好，具有良好的耐水性、耐化学性等。

This product has high purity, good lubricity, good water resistance and chemical resistance, etc.

技术指标/Index:

检测项目 Item	指标范围 Specification	测试方法 Test method
外观 Appearance	颗粒 Granule	目测 Visual
颜色 Color	≥+25	GB/T 3555
25℃针入度, 0.1mm Penetration at 25°C, 0.1mm	15-20	GB/T 4985
熔点, °C Melting point, °C	68-75	GB/T 2539
凝点, °C Solidification point, °C	67-70	SH/T 0132
油含量, % Oil content, %	<3	GB/T 3554
机械杂质和水 Mechanical impurities and water	0	目测 Visual

包装/Standard Packaging:

本产品为固体，包装规格为净重 25Kg 或 1 吨的编织袋或牛皮纸袋。

This product solid, packaged in woven bags or kraft paper bags with a net weight of 25kg or 1 ton.

以上所述及的产品应用信息真实可靠，但我们不对其做出任何形式的保证或担保。也不会给出本产品可用于任何违反专利或其他知识产权的建议或相似的理解或解释。对于本产品的任何应用技术问题请与本公司取得联系。电话:0533-6992006。

The above mentioned product application information is true and reliable, but we do not guarantee or guarantee it in any way. Nor will it give any suggestion or similar understanding or interpretation that this Product may be used in violation of any patent or other intellectual property rights. For any application technical problems of this product, please contact the company's research and development center. Telephone: 0533-6992006.

储存条件/Storage Condition:

本产品应存放于小于 30°C 干燥、阴凉、通风处，远离热源，避光干燥条件下。

Store in a dry, cool and ventilated place which is less than 30°C, far from heat and light.

保质期/Shelf Life:

3 年。 / 36 months.

以上所述及的产品应用信息真实可靠，但我们不对其做出任何方式的保证或担保。也不会给出本产品可用于任何违反专利或其他知识产权的建议或相似的理解或解释。对于本产品的任何应用技术问题请与本公司取得联系。电话：0533-6992006。

The above mentioned product application information is true and reliable, but we do not guarantee or guarantee it in any way. Nor will it give any suggestion or similar understanding or interpretation that this Product may be used in violation of any patent or other intellectual property rights. For any application technical problems of this product, please contact the company's research and development center. Telephone: 0533-6992006.